

Covid CLR-12D50125MOM3P Cleerline Fiber 12-Strand OM3 Plenum - 1000ft Box

Core Diameter	50.0 ± 2.5(µm)
Core Non-circularity	≤ 6(%)
Core / Hybrid Cladding Concentricity Error	≤ 3.0 (µm)
Hybrid Cladding Diameter	125 ± 0.7 (µm)
Hybrid Cladding Non-Circularity Error	≤ 3.0 (%)
Soft Peel Jacket Identifier Diameter	250 ± 0.7 (µm)
Coating Strip Force	100 (g)
Fiber Curl	≤ 2 (m)
Dynamic Fatigue Constant (Nd)	>30
Proof Test	100 (kpsi)
Bend Induced Attenuation at 1300 nm (100 turns around a mandrel of 75 mm diameter)	≤ 1.0 (dB)
Dynamic fatigue 23C, 41%RH	>30(nd)
Length	1.0 - 8.8 (Km)